

MANUFACTURED IN LAMAR, MO

The following information pertains ONLY to EverGrain® Composite Decking and is NOT APPLICABLE for EverGrain® Envision® Composite Decking.

CERTIFICATIONS/REPORTS

Code Compliant: ATI CCRR-0177†



CCRR-0177

TYPICAL PROPERTIES

PROPERTY	TEST METHOD	RESULT
Abrasion Resistance	ASTM D2394	0.004"/1000 rev.
Coefficient of Friction, Dry	ASTM F1679	0.61
Coefficient of Friction, Wet	ASTM F1679	0.67
Compressive Strength (parallel to length)	ASTM D198	6642 PSI
Flame Spread Index	ASTM E84	90
Hardness	ASTM D143	2408 lbs
Linear Coefficient of Thermal Expansion	ASTM D6341	1.34×10^{-5} in/in/°F
Shear Parallel to Grain	ASTM D143	2064 PSI
Smoke Developed Index	ASTM E84	400
Specific Gravity	ASTM D2395 (Method B)	1.14
Tensile Strength (parallel to length)	ASTM D198	>2495 PSI††
Water Absorption	ASTM D1037 (Method B)	0.84%

†A copy of this report can be obtained on tamko.com or by calling 800-641-4691.

††Test conducted using 70 mm x 22.5 mm x 610 mm specimens. Long dimension of specimens was oriented parallel to the length of the board. Specimens slipped from jaws preventing determination of ultimate tensile strength.

Information included in this product data sheet was current at time of printing. To obtain a copy of the most current version of this product data sheet, visit us online at tamko.com or call us at 800-641-4691. For information regarding or a copy of TAMKO's Limited Warranty, contact your local TAMKO representative, visit us online at tamko.com, or call us at 800-641-4691.



TAMKO Logo, EverGrain®, Envision® and TAMKO® are registered trademarks of TAMKO® Building Products, Inc.



Construction Materials International, Inc
 Address: 202 East 7th Avenue, Tampa, Florida 33602, USA
 Tel: (+1)813-287-8265 / Fax: (+1) 813-287-8144
 Email: sales@awg-llc.com / Web: www.cmi-us.com